





	INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PC						
(51)	International Patent Classification 6:		(11) International Publication Number: WO 98/21400				
	D21C 9/10, 9/14, 9/16	A1	(43) International Publication Date: 22 May 1998 (22.05.98)				
	International Application Number: PCT/SE International Filing Date: 29 October 1997 (European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB,				
(22)	International Fining Bate.						
(30)	Priority Data: 9604094-4 8 November 1996 (08.11.96) S	Published SE With international search report.				
(71)	Applicant (for all designated States except US): SUNI BRATOR INDUSTRIES AB [SE/SE]; S-851 94 S (SE).	OS DEF Sundsva	न- all				
(72) (75)	Inventor; and Inventor/Applicant (for US only): GERMGARD, Ulf Mastvägen 5, S-865 31 Alnö (SE).	[SE/SE	3);				
(74)	Agents: ROSENQUIST, Per, Olof et al.; Bergens Lindvall AB, P.O. Box 17704, S-118 93 Stockhol	tråhle m (SE)	&). 				
			· ·				
(54)	Title: PREBLEACHING OF PAPERPULP BEFORE	A PE	ROXIDE BLEACHING STAGE				
(57)	Abstract						
dige with	stion, and possibly oxygen bleaching, is subjected to a chelating agent at a high pH before a peroxide stage.	a mild	with enhanced efficiency for a chelating stage wherein the pulp after chlorine dioxide treatment at acidic pH, an alkalization and a treatment				
-	. n	, 3	ochate jukgling.				
		(1	octobe 20-0000.				
			200000				
	•	•	p. cf				
	t	(p. el 21th				
	PH 90 C	1	X /				
	T-40, 1606 CM	5					

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Amonia	FI	Finland	LT	Lithuania	SK	Slovakia
ΑT	Austria	FR	Prance	LU	Luxembourg	SN	Senegal
ΑU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Paso	GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Huggary	ML	Mali 4	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	ŪA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
-BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	tr	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	zw	Zimbabwe
CI	Cote d'Ivoire	KP	Democratic People's	NZ	New Zealand		5_5_5
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		•
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	L	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

10

1

PREBLEACHING OF PAPERPULP BEFORE A PEROXIDE BLEACHING STAGE

The present invention relates to a method for bleaching paper making pulp with peroxide, comprising a treatment stage with chelating agents. More specifically, the invention relates 5 to a method of improving the efficiency of a chelating stage according to which the pulp after digestion, and optionally oxygen bleaching, is subjected to a mild chlorine dioxide treatment at acidic pH, an alkalization and a treatment with a chelating agent before a peroxide stage.

Modern bleaching of paper making pulp has to be performed in an efficient way in order to keep the bleaching cost low while at the same time the strength and brightness shall be high. From environmental reasons the bleaching is performed with an increasing amount of oxygen and hydrogen peroxide which 15 leads to a decreasing use of chlorine containing chemicals and therefore the discharge of chloroorganic pollutants decreases. During later years there has been a growing demand for bleaching methods that are easy to close, i.e. that it shall be possible to return filtrates obtained at the bleaching to the closed part of the pulp mill, completely or partly, in order to reduce the discharge of substances having a negative effect on the environment.

The resulting waste water from a bleach plant normally consists of alkaline and acidic filtrates which are discharged 25 to the recipient, with or without preceding purification. In the normal case the acidic filtrate contains metal ions and transient metals from the wood and when the bleaching is performed with chlorine containing chemicals the filtrate also contains chloride ions. If chloride ions in larger amounts are 30 returned to the closed part of the pulp mill without a purging mechanism this can lead to processing equipment on the problematic corrosion, which can be especially noticeable in the soda recovery unit in the manufacture of pulp according to the sulphate process. At the same time chlorine containing bleaching chemicals are very effective, and thus such a bleaching of paper making pulp can be made comparatively lenient and at reasonable bleaching costs.

From environmental reasons it is interesting to be able to reduce the use of chlorine containing chemicals in the prebleaching, since chloroorganic substances to a large extent are formed in the prebleaching stage and since also the possibility of returning filtrate from the prebleaching stage is facilitated without the arise of the above discussed chloride problems.

It is well known per se to use a treatment of the pulp with 5 a chelating agent (Q-stage) in order to eliminate disturbing ions of transient metals, especially manganese, and thereby to increase the efficiency in a subsequent peroxide bleaching stage (P-stage). Such a method has been developed and commer-10 cialized under the name Lignox of Eka Nobel AB, Sweden. A treatment with chelating agents is normally made at a pH of 5 to 7 in order to give the best elimination of manganese. It is also known to treat pulp with a chelating agent in connection with a chlorine dioxide stage. The PCT application WO 96/06976 15 discloses a treatment with chelating agents directly before or after charging of chlorine dioxide without any intermediate wash with the object of being able to reduce the peroxide consumption and/or increase the brightness in the subsequent Pstage. The conditions in the Q- and D-stages in this method are said to be normal and only general intervals are given for the pH and other parameters. Through the PCT application WO 95/27100 it is also known to treat pulp with chelating agents in connection with a chlorine dioxide stage and according to this application the treatment with chelating agent can be done before, after or in the D-stage and preferably the treatment 25 with chelating agents and the chlorine dioxide bleaching are performed in one and the same stage at a pH of 3 - 7.

The object of the present invention is to solve the problems discussed above and relates to a method of bleaching paper making pulp at a highly closed prebleaching, comprising a pretreatment of the pulp with chlorine dioxide, followed by an alkalization and thereafter a treatment with chelating agents before washing directly followed by a peroxide bleaching stage. The method is more closely defined in the following claims.

According to the present method an introductory mild treatment with chlorine dioxide is performed, wherein the chlorine dioxide is added primarily with the object of preoxidizing the pulp so that metals disturbing the process, primarily transient metals and especially manganese, are more exposed and can be bound more easily by chelating agents being

added in a subsequent stage before a peroxide bleaching stage. The addition of chlorine dioxide in the introductory treatment shall be so low that it does not cause noticeable problems in the recovery when the filtrate is returned. After that the 5 added chlorine dioxide has been consumed a pH increase is accomplished before the addition of a chelating agent. By this alkalization a disintegration of possible residual amounts of chlorine dioxide in the pulp into inactive substances is obtained. The alkalization also leads to that calcium is 10 attached to the pulp which is essential in order to prevent an accumulation of calcium in the closed part of the bleaching. An accumulation of calcium ions can namely lead to problematic deposits and incrust formation on the processing equipment. The bleaching in subsequent peroxide bleaching stages can, thanks 15 to the preceding treatment according to the invention, be made more efficient and result in a pulp with good strength. Further, the method is environmentally advantageous regarding the formation of chloroorganic substances and advantageous in view of corrosion and scaling in the processing equipment 20 without the need for costly purging methods, neither for calcium nor for chloride.

The method according to the present invention can be applied in bleaching of paper making pulp of softwood or hardwood type. The method can be applied for kraft as well as sulphite pulp but is of greatest interest for kraft pulp in view of that this contains more calcium ions which can create problems.

After delignification and washing, in modern pulp mills the pulp is normally treated with oxygen and alkali in an oxygen stage for further delignification, and dissolved wood substance is subsequently separated in a washing stage. The actual bleaching according to the present invention is subsequently started with a mild chlorine dioxide treatment wherein the amount of charged chlorine dioxide is maximum 15 kg, calculated as kg active chlorine, per ton pulp. The chlorine dioxide charge should be low in order to eliminate the need of expensive purging processes for chloride when the filtrate is returned and the limit is hereby a return of maximum 2 - 3 kg chloride, calculated as kg Cl, per ton pulp. The chlorine dioxide charge in the introductory treatment, the prebleaching,

WO 98/21400 PCT/SE97/01810

4

lies thus advantageously within the interval from 2 to 15 kg/ton pulp and preferably within the interval from 5 to 10 kg/ton, where the chlorine dioxide is calculated as active chlorine. The chlorine dioxide charge depends to some extent on the preceding treatment of the pulp. If the pulp after digestion and washing has been oxygen delignified the amounts may lie in the lower part of the given intervals and in the upper part if it has not been treated with oxygen in a precedent stage. It can be noted that normal charges at prebleaching with chlorine dioxide is about 20 to about 40 kg/ton if the pulp is oxygen-delignified and 40 to 70 kg/ton if the pulp has not been oxygen delignified. The prebleaching with chlorine dioxide is performed as is conventional at acidic pH, normally from 2 to 4. The temperature in the stage can be kept between about 40 and about 90°C and the stage can be performed at usual pulp consistencys of 8 to 16% and with residence times, which can be from 5 minutes to 1 hour.

After the chlorine dioxide treatment follows according to the present method an alkalization stage, which should be done to a pH of at least 8.5. The alkalization can suitably be done with NaOH. Suitably the alkalization is done to a pH of at least 9.5. The upper limit for the pH value is among other things determined by the risk of increased amount of redeposited manganese on the pulp and suitably it does not exceed 11. The alkalization is, as mentioned above, important, partly in order to inactivate possible remaining amounts of chlorine dioxide in the pulp and chlorine dioxide deteriorates into chlorate and chlorite at high pH values, thereby no remaining chemical reacts with the chelating agent added later, and partly because calcium is redeposited on the pulp at higher pH values.

After the alkalization, a Q-stage is performed, i.e. a chelating stage, at said high pH value, minimum 8.5. The chelating agent will hereby keep ions of transient metals, primarily manganese, in solution while calcium deposits on the pulp, which, as already mentioned, is advantageous in order to prevent or reduce deposition of calcium salts which can lead to clogging of pipes and other equipment and reduced function of the process equipment.

As chelating agents can be used any such agent which binds

` , 10

742

the actual disturbing trace metals, primarily manganese, copper and iron. Suitable chelating agents are aminocarboxylic acids, such as e.g. ethylenediaminetetra-acetic acid (EDTA), diethylenetriaminepenta-acetic acid (DTPA) and triethylene-5 tetraaminehexa-acetic acid (TTHA), aminophosphonic acids, such as e.g. ethylenediaminetetramethylene-phosphonic acid, phosphonic acids, such as e.g. hydroxyethyldi-phosphonic acids, and polyphosphates. In practice, usually EDTA or DTPA are used as chelating agent and in the present method DTPA is preferably 10 used. The chelating stage is usually performed at elevated temperature, from about 40°C up to 95°C and the amount of chelating agent, calculated as pure product, should be at least 0.5 kg/ton pulp but can be to 5 kg/ton. Preferably it lies within the interval from 1 to 2 kg/ton. The pulp consistency in 15 the chelating stage is not critical but can vary e.g. from 2 to 20 % by weight cellulose containing material. Suitably, however, the consistency lies within the interval from 8 to 16 % in order to suit conventional processing equipment. The treatment time in the Q-stage depends on among other things the 20 temperature and should be at least 5 minutes and preferably at least 60 minutes and can if necessary be up to several hours.

The actual additions of the chemicals, chlorine dioxide, alkali and chelating agent, in the above described three stage treatment can e.g. be made in one or several mixers, pumps or 25 dilution circulations. The three stages of pretreatment are performed in a sequence, without intermediate washing. The pulp treated according to the above is subsequently, after washing, transferred to a peroxide bleaching stage (P-stage), wherein usually hydrogen peroxide is used, even if, in principal, it is 30 possible to use other peroxides. The P-stage can be performed in a conventional way, i.e. at alkaline pH, usually within the pH-interval 10 - 12, a temperature from about 50 to about 110°C and with a peroxide addition, hydrogen peroxide or a corresponding amount of another peroxide, which usually lies within 35 the interval 5 to 50 kg/ton pulp. The peroxide stage can, if desired, be complemented with an oxygen addition and then suitably of at least 1 kg/ton pulp. The oxygen addition in this stage suitably amounts to maximum 20 kg/ton pulp and preferably to maximum 10 kg/ton pulp. The pulp consistency in the P-stage normally lies within the interval from 8 to 16 %.

After the P-stage the pulp is washed and is normally transferred to further bleaching stages, e.g. one or several chlorine dioxide stages or a further peroxide stage.

The method according to the present invention is well

suited for use in a hardly closed bleaching plant wherein all
precedent stages are alkaline. The filtrate from the P-stage
can be returned through the pretreatment stage directly to the
digester wash or to the wash of a subsequent oxygen stage.

Claims

- A method for bleaching of paper making pulp, characterized in that the pulp, before a peroxide bleaching stage, is subjected to a prebleaching treatment in three stages
 without intermediate washes, whereby the pulp is first treated with chlorine dioxide in an amount of maximum 15 kg/ton, calculated as kg active chlorine per ton, at acidic pH, thereafter the pulp is made alkaline to a pH of minimum 8.5, and is then treated with a chelating agent at a pH of minimum
 8.5, whereupon the pulp is washed.
 - 2. A method according to claim 1, characterized in that the pulp is treated with chlorine dioxide in an amount of from 2 to 15 kg/ton.
- 3. A method according to claim 1 or 2, characterized in 15 that the chlorine dioxide treatment is made at a pH not exceeding 4.
 - 4. A method according to claim 1, characterized in that the alkalization is made to a pH of minimum 9.5.
- 5. A method according to claim 1, characterized in that 20 diethylenetriaminepenta-acetic acid is added as chelating agent.
 - 6. A method according to any of the preceding claims, characterized in that the addition of the three chemicals chlorine dioxide, alkali and chelating agent is made in one or several mixers, pumps or dilution circulations.
 - 7. A method according to claim 1, characterized in that the peroxide bleaching stage is performed in the presence of oxygen.
- 8. A method according to any of the preceding claims,


 30 characterized in that the filtrate from the peroxide stage is returned through the pretreatment stage and thereafter to a preceding stage.
 - A method according to any of the preceding stages, characterized in that the pulp is a kraft pulp.

INTERNATIONAL SEARCH REPORT

International application No.

		PL1/3E 9/	,01810 '					
A. CLAS	SSIFICATION OF SUBJECT MATTER							
IPC6: D21C 9/10, D21C 9/14, D21C 9/16 According to International Patent Classification (IPC) or to both national classification and IPC								
B. FIEL	B. FIELDS SEARCHED							
1	Minimum documentation searched (classification system followed by classification symbols)							
	IPC6: D21C							
Documents	ation searched other than minimum documentation to	the extent that such documents are included	in the fields searched					
SE,DK,FI,NO classes as above								
Electronic	data base consulted during the international search (na	me of data base and, where practicable, sear	ch terms used)					
EPODOC	EPODOC, WPI							
C. DOC	JMENTS CONSIDERED TO BE RELEVANT							
Category*	Citation of document, with indication, where a	ppropriate, of the relevant passages	Relevant to claim No.					
A	WO 9606976 A1 (SUNDS DEFIBRATO 7 March 1996 (07.03.96), p. page 4, figure 2, abstract	R INDUSTRIES AB), age 2, line 1 - line 20;	1-9					
A	 WO 9625552 A1 (A.AHLSTROM CORPO	DRATION)	1-9					
	22 August 1996 (22.08.96), line 1 - line 7; page 15, page 16, line 3, figures 1	page 11, line 33 - line 35:	1 9					
A	WO 9527100 A1 (MO OCH DOMSJÖ AK 12 October 1995 (12.10.95)	TIEBOLAG),	1-9					
ļ								
Furthe	er documents are listed in the continuation of Bo	x C. X See patent family anno	x.					
"A" documen	estegories of cited documents at defining the general state of the art which is not considered	T later document published after the int date and not in conflict with the appli	cation but cited to understand					
"E" erlier do	particular relevance comment but published on or after the international filing date at which may throw doubts on priority claim(s) or which is	"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive						
special n	establish the publication date of another citation or other eason (as specified) at referring to an oral disclosure, use, exhibition or other	"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is						
"P" documen	nt published prior to the international filing date but later than	combined with one or more other such documents, such combination						
Date of the	actual completion of the international search	Date of mailing of the international s						
27 January 1998 12.02.1998								
	nailing address of the ISA/	Authorized officer						
Swedish Patent Office								
Box 5055, S-102 42 STOCKHOLM Facsimile No. +46 8 666 02 86 Marianne Bratsberg Telephone No. +46 8 782 25 00								
		Telephone No. + 46 8 782 25 00						

Form PCT/ISA/210 (second sheet) (July 1992)



Information on patent family members

International application No. 07/01/98 | PCT/SE 97/01810 |

cit	Patent document cited in search report		Publication date	Patent family member(s)		Publicati dale	on	
WO	9606976	A1	07/03/96	UA	3401795	A 22/03/96		
				CA	2197771			
				EP	0778909			
				FI	970821			
				NO	970907	, - ,,,		
				SE	9402885			
				ZA	9507070			
WO	9625552	A1	22/08/96	CA	2211223	22/08/96	-	
			,,	FI	950749			
		-		FΙ	953343		1	
				SE	9502087	18/08/96	- [
•				AU	5823896		ł	
				AU	6128196 A		I	
				FI	953064 A		ĺ	
				FI	954407 A			
				WO	9700997 A	09/01/97	1	
				MO	9700998 A	09/01/97	1	
				WO	9701074 A	09/01/97	••	
WO	9527100	A1	12/10/95	ΑU	1206995 A	19/06/95		
				AU	2226495 A			
				CA	2185808 A	,,	Ì	
				EP	0754258 A	22/01/97		
				FI	963985 A	04/10/96]	
				NO	964223 A	04/10/96		
				NZ	283828 A	26/05/97		
				SE	502706 C	11/12/95	}	
	~~			SE	9401125 A	06/10/95	1	
							ŀ	